



Acids										
Acetic acid	CH ₃ COOH	Conc. > 98%	2min 1 h 24 h	A0 A0 A0	B0 B0 B1	C0 C0 C0	D0 D0 D0	E0 E0 E0	F0 F0 F0	G0 G0 G0
Chromic acid	H ₂ CrO ₄	40%	2min 1 h 24 h	A0 A0 A6	B0 B0 B1	C0 C0 C0	D0 D0 D0	E0 E0 E0	F0 F0 F0	G0 G0 G0
Citric acid	C ₆ H ₈ O ₇	50%	1 h 24 h	A0 A0	B0 B0	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Hydrochloric acid	HCl	Conc. 37%	2min 1 h 24 h	A0 A5 A5	B0 B1 B1	C0 C0 C0	D0 D0 D0	E0 E0 E0	F0 F0 F0	G0 G0 G0
Hydrofluoric acid	HF	40%	2min 1 h 24 h	A0 A0 A1	B0 B0 B1	C0 C0 C1	D0 D0 D1	E0 E0 E0	F0 F0 F0	G0 G0 G0
Phosphoric acid	H ₃ PO ₄	Conc. > 85%	2min 1 h 24 h	A0 A0 A0	B0 B1 B2	C0 C0 C1	D0 D0 D0	E0 E0 E0	F0 F0 F0	G0 G0 G0
Phosphoric acid	H ₃ PO ₄	38%	24 h	A0	B0	C0	D0	E0	F0	G0
Lactic acid	C ₃ H ₆ O ₃	Conc. 90%	1 h 24 h	A0 A0	B0 B1	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Nitric acid	HNO ₃	Conc. 65%	2min 1 h 24 h	A5 A6 A6	B1 B2 B2	C0 C1 C1	D0 D0 D1	E0 E0 E1	F0 F5 F6	G0 G0 G0
Nitric acid	HNO ₃	30%	2min 1 h 24 h	A0 A5 A5	B0 B1 B2	C0 C0 C1	D0 D0 D0	E0 E0 E0	F0 F0 F0	G0 G0 G0
Oxalic acid	C ₂ H ₂ O ₄	10%	1 h 24 h	A0 A0	B0 B0	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Sulphuric acid	H ₂ SO ₄	Conc. 98%	2min 1 h 24 h	A5 A6 A6	B1 B2 B2	C0 C1 C1	D0 D1 D2	E0 E1 E1	F0 F5 F5	G0 G0 G0
Sulphuric acid	H ₂ SO ₄	30%	1 h 24 h	A0 A0	B0 B1	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Organic solvents										
Acetone	C ₃ H ₆ O		2min 1 h 24 h	A0 A0 A0	B0 B1 B1	C0 C1 C1	D0 D0 D1	E0 E0 E5	F0 F0 F5	G0 G0 G0
Acetonitrile	CH ₃ CN		2min 1 h 24 h	A0 A0 A0	B0 B0 B0	C0 C0 C0	D0 D0 D0	E0 E0 E5	F0 F0 F5	G0 G0 G0
Carbon tetrachloride	CCl ₄		2min 1 h 24 h	A0 A0 A0	B0 B0 B0	C0 C0 C0	D0 D0 D0	E0 E0 E0	F0 F1* F1*	G0 G0 G0
Chloroform	CHCl ₃		2min 1 h 24 h	A0 A0 A0	B1 B2 B2	C0 C1 C1	D0 D0 D1	E0 E5 E5	F0 F0 F5	G0 G0 G0
Cyclohexane	C ₆ H ₁₂		2min 1 h 24 h	A0 A0 A0	B0 B0 B0	C0 C0 C0	D0 D0 D0	E0 E0 E0	F0 F0 F0	G0 G0 G0
Cyclohexanone	C ₆ H ₁₀ O		2 min 1 h 24 h	A0 A0 A0	B1 B2 B2	C1 C2 C2	D0 D3 D3	E0 E5 E6	F0 F0 F6	G0 G0 H
Dichloroethylene	C ₂ H ₂ Cl ₂		2min 1 h 24 h	A0 A0 A0	B0 B0 B0	C0 C0 C0	D0 D0 D0	E0 E0 E5	F0 F0 F5	G0 G0 G0
Methylene Chloride	CH ₂ Cl ₂		2min 1 h 24 h	A0 A0 A0	B1 B2 B2	C1 C1 C1	D0 D0 D0	E0 E5 E5	F0 F5 F5	G0 G0 H*
Ethanol	C ₂ H ₅ OH		1 h 24 h	A0 A0	B0 B1	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0

Organic solvents,cont.								
Ethyl acetate	C ₄ H ₈ O ₂	2min	A0	B0	C0	D0	E0	F0 G0
		1 h	A0	B1	C1	D0	E5	F1* G0
		24 h	A0	B1	C1	D0	E5	F5 G0
Ethylene glycol	C ₂ H ₆ O ₂	24 h	A0	B0	C0	D0	E0	F0 G0
Diethyl ether	(C ₂ H ₅) ₂ O	2 min	A0	B0	C0	D0	E0	F0 G0
		1 h	A0	B0	C0	D0	E0	F1* G0
		24 h	A0	B0	C0	D0	E0	F5 G0
n-Hexane	C ₆ H ₁₄	1 h	A0	B0	C0	D0	E0	F0 G0
		24 h	A0	B0	C0	D0	E0	F0 G0
Formaldehydesolution	CH ₂ O 37 %	24 h	A0	B0	C0	D0	E0	F0 G0
Methanol	CH ₃ OH	1 h	A0	B0	C0	D0	E0	F0 G0
		24 h	A0	B1	C0	D0	E0	F0 G0
Methyl ethyl ketone	C ₄ H ₈ O	2 min	A0	B1	C1	D0	E0	F0 G0
		1 h	A0	B2	C2	D2	E5	F0 G0 H*
		24 h	A0	B2	C2	D3	E5	F5 G0 H*
Pet.ether (Ligroin)	CAS-nr: 80-110°C	1 h	A0	B0	C0	D0	E0	F0 G0
8032-32-4		24 h	A0	B0	C0	D0	E0	F0 G0
		2min	A0	B0	C0	D0	E0	F0 G0
		1 h	A0	B0	C0	D0	E0	F1* G0
Tetrachloroethylene	C ₂ Cl ₄	24 h	A0	B0	C0	D0	E5	F1* G0
		2min	A0	B0	C0	D0	E0	F0 G0
		1 h	A0	B0	C0	D0	E0	F1* G0
Toluene	C ₇ H ₈	2min	A0	B0	C0	D0	E0	F0 G0
		1 h	A0	B1	C0	D0	E0	F1* G0
		24 h	A0	B2	C1	D0	E5	F5 G0
Trichlorethylene	C ₂ HCl ₃	2min	A0	B0	C0	D0	E0	F0 G0
		1 h	A0	B1	C1	D0	E5	F1* G0
		24 h	A0	B1	C1	D0	E5	F5 G0
White spirit	EG/EC/EF-no: 265-191-7	2min	A0	B0	C0	D0	E0	F0 G0
		1 h	A0	B0	C0	D0	E0	F0 G0
		24 h	A0	B0	C0	D0	E0	F0 G0
Xylene	C ₈ H ₁₀	2 min	A0	B0	C0	D0	E0	F0 G0
		1 h	A0	B0	C0	D0	E0	F0 G0
		24 h	A0	B1	C1	D0	E5	F5 G0
Alkali (Bases)								
Ammonia solution	NH ₃ 25%	1 h	A0	B0	C0	D0	E0	F0 G0
		24 h	A0	B0	C0	D0	E0	F0 G0
Calcium hydroxide	Ca(OH) ₂ 10%	1 h	A0	B0	C0	D0	E0	F0 G0
		24 h	A0	B0	C0	D0	E0	F0 G0
Sodium hydroxide	NaOH 50%	1 h	A0	B0	C0	D0	E0	F0 G0
		24 h	A0	B0	C0	D0	E0	F0 G0
Sodium hydroxide	NaOH 10%	1 h	A0	B1	C0	D0	E0	F0 G0
		24 h	A0	B2	C0	D0	E0	F0 G0 H
Salt solutions								
Ammonium carbonate	(NH ₄) ₂ CO ₃ 10%	1 h	A0	B0	C0	D0	E0	F0 G0
		24 h	A0	B0	C0	D0	E0	F0 G0
Ammonium iron (III) sulphate	NH ₄ Fe(SO ₄) ₂ 10%	1 h	A0	B0	C0	D0	E0	F0 G0
		24 h	A0	B0	C0	D0	E0	F0 G0
Calcium Chloride	CaCl ₂ Saturated	24 h	A0	B0	C0	D0	E0	F0 G0
Cobaltous chloride	CoCl ₂ 10%	24 h	A0	B0	C0	D0	E0	F0 G0
Copper (II) sulphate	CuSO ₄ 10%	1 h	A0	B0	C0	D0	E0	F0 G0
		24 h	A0	B0	C0	D0	E0	F0 G0
Ferrous (II) chloride	FeCl ₂ 10%	1 h	A0	B0	C0	D0	E0	F0 G0
		24 h	A1	B0	C0	D0	E0	F0 G0
Ferric (III) chloride	FeCl ₃ 10%	1 h	A0	B0	C0	D0	E0	F0 G0
		24 h	A1	B0	C0	D0	E0	F0 G0
Potassium iodide	KI 10%	24 h	A0	B0	C0	D0	E0	F0 G0
Potassium oxalate	K ₂ C ₂ O ₄ 10%	24 h	A0	B0	C0	D0	E0	F0 G0
Potassium permanagnate	KMnO ₄ 5% in H ₂ O	2 min	A5	B0	C0	D0	E0	F0 G0
		1 h	A6	B0	C0	D0	E0	F0 G0
Silver nitrate	AgNO ₃ 2%	1 h	A0	B0	C0	D0	E0	F0 G0
		24 h	A5	B0	C0	D0	E0	F0 G0

Salt solutions cont.										
Sodium carbonate	Na ₂ CO ₃	20%	1 h	A0	B0	C0	D0	E0	F0	G0
			24 h	A0	B0	C0	D0	E0	F0	G0
Sodium thiosulphate	Na ₂ S ₂ O ₃	10%	1 h	A0	B0	C0	D0	E0	F0	G0
			24 h	A0	B1	C0	D0	E0	F0	G0
Sodium sulphite	Na ₂ SO ₃	10%	24 h	A0	B0	C0	D0	E0	F0	G0
Medical chemicals										
Aniline blue		2,5% in ethanol	1 h 24 h	A6 A6	B0 B0	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Betadine skin cleanser		75mg/ml	1 h 24 h	A0 A5	B0 B0	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Bromcresol green		0,04 %	24 h	A0	B0	C0	D0	E0	F0	G0
Eosin		1 % in Ethanol	1 h 24 h	A6 A6	B0 B0	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Glutaraldehyde		25%	1 h 24 h	A0 A0	B0 B0	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Hematoxylin		5%	1 h 24 h	A0 A5	B0 B0	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Hibitane		0,5%	1 h 24 h	A5 A6	B0 B0	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Iodine	I ₂	2 % in ethanol	2min 1 h	A6 A6	B0 B0	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Iodoform		1% in ethanol	1 h 24 h	A6 A6	B0 B0	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Methylrosanilinium		0,1%	1 h 24 h	A0 A6	B0 B0	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Disinfectants/cleaning compounds										
Product		Manuf./Rep.								
Buraton 10F	Schülke & Mayr	1% 10%	24 h	A0 A0	B0 B0	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
"-										
Citrosteril	Fresenius	Conc.	24 h	A0	B0	C0	D0	E0	F0	G0
Debisan	Nordex	1 %	24 h	A0	B0	C0	D0	E0	F0	G0
"-		10%	24 h	A0	B0	C0	D0	E0	F0	G0
Decon-Spore 200 Plus	Veltek Associates, Inc	0,5 % 5 %	24 h 24 h	A0 A0	B0 B0	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Dialox	Gambro	Conc.	24 h	A0	B1	C0	D0	E0	F0	G0
Gevisol	Schülke & Mayr	0,5% 5%	24 h	A5 A6	B0 B0	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Incidur	Henkel	0,5% 3%	24 h	A0 A0	B0 B0	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Lycetol AF	Schülke & Mayr	1% 5%	24 h	A0 A5	B0 B0	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Melsept	B Braun	1% 5%	24 h	A0 A0	B0 B0	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Perform	Schülke & Mayr	0,75% 2,5%	24 h	A0 A0	B0 B0	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Sekumatic	Henkel	0,5% 5%	24 h	A0 A0	B0 B1	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Sekusept Plus	Henkel	1% 5%	24 h	A0 A0	B0 B0	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Spitacid	Henkel	Conc.	1 h 24 h	A0 A0	B0 B1	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Terralin N	Schülke & Mayr	1% 10% 10%	24 h 1 h 24 h	A0 A0 A0	B0 B0 B1	C0 C0 C0	D0 D0 D0	E0 E0 E0	F0 F0 F0	G0 G0 G0
Titol KF	B. Braun	3% 10%	24 h 24 h	A0 A0	B0 B1	C0 C0	D0 D0	E0 E0	F0 F0	G0 G0
Virkon S	Sterisol AB	1% 2,5%	24 h	A0	B0	C0	D0	E0	F0	G0
Incidin Plus	Ecolab	1% 5%	24 h	A0	B0	C0	D0	E0	F0	G0

Disinfectants/cleaning compounds. cont.										
Product	Manuf./Rep.									
Incidin Extra N	Ecolab	1%	24 h	A0	B0	C0	D0	E0	F0	G0
		5%	24 h	A0	B0	C0	D0	E0	F0	G0
Mikrobac forte	BODE Chemi	1%	24 h	A0	B0	C0	D0	E0	F0	G0
		5%	24 h	A0	B0	C0	D0	E0	F0	G0
Hexaquart plus	B. Braun	1%	24 h	A0	B0	C0	D0	E0	F0	G0
		2,5%	24 h	A0	B0	C0	D0	E0	F0	G0
Miscellaneous chemicals										
EDTA	C ₁₀ H ₁₆ N ₂ O ₈	10%	24 h	A0	B0	C0	D0	E0	F0	G0
Glycerol			24 h	A0	B0	C0	D0	E0	F0	G0
Hydrogen peroxide	H ₂ O ₂	35%	1 h	A0	B0	C0	D0	E0	F0	G0
			24 h	A0	B0	C0	D0	E0	F0	G0
Olive oil			24 h	A0	B0	C0	D0	E0	F0	G0
Phenol	C ₆ H ₆ O	5%	2 min	A0	B0	C0	D0	E0	F0	G0
			1 h	A0	B1	C0	D0	E0	F0	G0
			24 h	A0	B1	C0	D0	E0	F0	G0
Sodium hypochlorite	NaOCl	12%	1 h	A0	B0	C0	D0	E0	F0	G0
			24 h	A0	B1	C0	D0	E0	F0	G0
Brake fluid	APE	Conc	1 h	A0	B0	C0	D0	E0	F0	G0
Super DOT 4	Components AB		24 h	A0	B0	C0	D1	E5	F0	G0
Hydraulic fluid	Mobil	Conc	1 h	A0	B0	C0	D0	E0	F0	G0
			24 h	A0	B0	C0	D0	E0	F0	G0

*The swelling disappears after 1-2 days.

H* Slight damage to polyurethane surface.

H Total damage to polyurethane surface.